

PRODUCT DATA SHEET

EDGE CHEM JAMAICA LIMITED
18 Carifta Avenue
Kingston 11, Jamaica
Tel: (876) 937-3831-4 Fax: 937-3838
E-mail: edge@cwjamaica.com
Website: www.edgechem.com

ACID CATALYZED HIGH GLOSS CLEAR LACQUER

Rev. 3 T.D.S.

DESCRIPTION

EdgeChem A.C. Lacquer is a tough, high gloss, clear finish which offers resistance to alcohol, water spotting and blushing.

PERFORMANCE FEATURES

- High build
- High gloss
- Fast drying
- No critical re-coat time

PHYSICAL PROPERTIES

Gloss	:	94% at 60°
Specific Gravity	:	0.99
Viscosity	:	93-94s (#4 Ford Cup at 25°C)
Flash Point	:	25°C
Colour	:	Clear Amber
Drying Time:-		
To Touch	:	20-30 minutes
To Re-coat	:	5-10 minutes
Hard dry	:	Overnight

COVERAGE RATE


Approximately 350 square feet per gallon.

SUGGESTED USES

For use on wood and furniture products.

SURFACE PREPARATION

Surface must be dry and free of grease, oil and dirt. Moisture content of wood must not exceed 8% Relative Humidity. For optimum results A.C. Lacquer should be used over EdgeChem Sanding Sealer, sanded to a smooth finish with 400-600 grit sandpaper. Badly damaged or poor surface must be stripped to bare wood and treated as new.



PRODUCT DATA SHEET

EDGE CHEM JAMAICA LIMITED
18 Carifta Avenue
Kingston 11, Jamaica
Tel: (876) 937-3831-4 Fax: 937-3838
E-mail: edge@cwjamaica.com
Website: www.edgechem.com

ACID CATALYZED HIGH GLOSS CLEAR LACQUER

Rev. 3 T.D.S.

APPLICATION

Stir contents well. Mixing ratio -12 parts A.C. Lacquer: 1 part A.C. Lacquer Catalyst. Reduce 20% with EdgeChem Lacquer Thinner five (5) parts catalyzed Lacquer to one (1) part thinner for spraying if so desired. Apply 2-3 coats of mixture allowing for a flash off time of ten (10) minutes between coats.

Pot Life: 4-6 hours

SHELF LIFE

1 year

CLEAN-UP

Clean up with EdgeChem Cleaning solvent or EdgeChem Lacquer Thinner.

