

## PRODUCT DATA SHEET

EDGE CHEM JAMAICA LIMITED  
18 Carifta Avenue  
Kingston 11, Jamaica  
Tel: (876) 937-3831-4 Fax: 937-3838  
E-mail: [edge@cwjamaica.com](mailto:edge@cwjamaica.com)  
Website: [www.edgechem.com](http://www.edgechem.com)

# EDGE COLAC (Chinese Lacquer)

Rev. 2 T.D.S.

### DESCRIPTION

EdgeChem Edgecolac Chinese lacquer is a tough, high gloss medium/long oil alkyd maintenance enamel. It is suitable for interior and exterior use on metal and wood. Edgecolac Chinese lacquer is free of lead, chromate and other toxic heavy metals making it suitable for use on cribs, toys and children furniture.

### PERFORMANCE FEATURES

- Tough Finish
- High Gloss
- Low toxicity
- Interior and exterior use
- Excellent gloss retention and durability

### PHYSICAL PROPERTIES

Gloss	:	>85% at 60°
Viscosity	:	90-100s
Specific Gravity	:	0.96-1.11
Flash Point	:	25-28°C (based on major solvent component)
Coverage	:	380-400 sq.ft.
Colors	:	White, Black, Customer Specified
Drying Time:-		
Dust Free	:	10-15 minutes
Tack Free	:	30-45 minutes
Dry to Handle	:	4 hours
Hard dry	:	24 hours
Re-coat time	:	12 hours

### SUGGESTED USES


For use on steel, masonry, wood, galvanized steel and aluminum.

### SURFACE PREPARATION

Clean surface free of dirt, oil, flakes or loose paint. Galvanized steel and aluminum must be primed with an etching or epoxy primer.

For wood and masonry, sand using 180g sandpaper, remove dust and flake.

Reduce with Oil Paint Thinner if necessary.



## PRODUCT DATA SHEET

EDGE CHEM JAMAICA LIMITED  
18 Carifta Avenue  
Kingston 11, Jamaica  
Tel: (876) 937-3831-4 Fax: 937-3838  
E-mail: [edge@cwjamaica.com](mailto:edge@cwjamaica.com)  
Website: [www.edgechem.com](http://www.edgechem.com)

# EDGE COLAC (Chinese Lacquer)

Rev. 2

T.D.S.

### APPLICATION

Spray or brush two (2) coats allowing five (5) minutes for flash off between coats. Spraying Pressure is 35-40 psi.

### SHELF LIFE

2 Years

### CLEAN-UP

Clean up with EdgeChem Oil Paint Thinner.

