

PRODUCT DATA SHEET

EDGE CHEM JAMAICA LIMITED
18 Carifta Avenue
Kingston 11, Jamaica
Tel: (876) 937-3831-4 Fax: 937-3838
E-mail: edge@cwjamaica.com
Website: www.edgechem.com

EDGECOLAC SPARKLING SILVER

Rev. 2

T.D.S.

DESCRIPTION

EdgeChem Edgecolac Sparkling Silver is a tough, high gloss medium/long oil alkyd ready mix aluminum paint. It contains a fine grade leafing aluminum paste and is suitable for use on interior and exterior wood, masonry, and primed metal surfaces.

PERFORMANCE FEATURES

- Tough Finish
- High Gloss
- Low toxicity
- Interior and exterior use
- Excellent gloss retention and durability

PHYSICAL PROPERTIES

Gloss	:	>85% at 60°
Viscosity	:	90-100s
Specific Gravity	:	0.96-1.11
Flash Point	:	25-28°C (based on major solvent component)
Color	:	Sparkling Silver
Drying Time:-		
Dust Free	:	10-15 minutes
Tack Free	:	1 hour
Dry to Handle	:	4 hours
Hard dry	:	12 hours
Re-coat time	:	4-6 hours

COVERAGE RATE


Approximately 380-400 square feet per gallon.

SUGGESTED USES

For use on primed metal, masonry, and wood.

SURFACE PREPARATION

Clean surface free of dirt, oil, flakes or loose paint, rust and wax and ensure surface is dry before application of EdgeChem sparkling Silver. For previously painted surfaces remove all loose, peeling or cracking paint. Remove rust by scraping or with a wire brush. Roughen all glossy surfaces to ensure proper adhesion of the topcoat.



PRODUCT DATA SHEET

EDGE CHEM JAMAICA LIMITED
18 Carifta Avenue
Kingston 11, Jamaica
Tel: (876) 937-3831-4 Fax: 937-3838
E-mail: edge@cwjamaica.com
Website: www.edgechem.com

EDGE COLAC SPARKLING SILVER

Rev. 2

T.D.S.

APPLICATION

Wood: Apply directly to wood.

Concrete: Apply directly to concrete no priming necessary.

Steel: Apply a suitable primer such as EdgeChem Red Oxide Primer before applying Sparkling Silver.

Galvanized Metal: Allow new zinc sheets to weather for months. If weathering is not possible etch with a suitable etching solution before applying Sparkling Silver. Rust spots must be wire brushed and primed with EdgeChem Red Oxide Primer before applying Sparkling Silver.

Reduction not required for brush or roller application. Thin with EdgeChem Industrial Thinner for spray application.

SHELF LIFE

2 years

CLEAN-UP

Clean up with EdgeChem Industrial Thinner.

