

PRODUCT DATA SHEET

EDGE CHEM JAMAICA LIMITED
18 Carifta Avenue
Kingston 11, Jamaica
Tel: (876) 937-3831-4 Fax: 937-3838
E-mail: edge@cwjamaica.com
Website: www.edgechem.com

NITROCELLULOSE SANDING SEALER

Rev. 2

T.D.S.

DESCRIPTION

EdgeChem Sanding Sealer is a nitrocellulose based wood sealer which ensures adhesion of top coat to substrate resists moisture and eliminates seepage of finishes into the substrate.

PERFORMANCE FEATURES

- Fast air drying
- Easy sanding
- Enhance adhesion
- High sealing properties
- Good build

PHYSICAL PROPERTIES


Specific Gravity	:	0.91 g
Viscosity	:	200s (#4 Ford Cup at 25°C)
Flash Point	:	5°C (40°F)
Colour	:	Opaque Amber
Drying Time:-		
To Touch	:	5 minutes
To Re-coat	:	10 minutes
Dry to Sand	:	30 minutes

SUGGESTED USES

To seal the pores wooden surfaces to give a sound surface to apply Lacquer or Varnish.

SURFACE PREPARATION

- New wood** - should be properly cured and finely sanded with 400-600 grit sand paper. Remove sanding debris from the surface.
- Refinishing** – If surface is in good condition, remove all polish or wax. Sand to a matte finish and remove all sanding debris. Test spray to check compatibility of sealer with old finish and for the presence of silicone (fish eye).



PRODUCT DATA SHEET

EDGE CHEM JAMAICA LIMITED
18 Carifta Avenue
Kingston 11, Jamaica
Tel: (876) 937-3831-4 Fax: 937-3838
E-mail: edge@cwjamaica.com
Website: www.edgechem.com

NITROCELLULOSE SANDING SEALER

Rev. 2

T.D.S.

APPLICATION

EdgeChem Sanding Sealer should be reduced with EdgeChem Lacquer Thinner in the ratio of 2:1, and sprayed at about 50 psi on prepared wood. Apply normally 2-3 coats at ten (10) minutes intervals. To prevent blushing due to high humidity use EdgeChem Retarder as directed. Allow at least thirty (30) minutes before sanding with very fine sand paper. Remove all dust with a blow gun before top coating with EdgeChem High Gloss Lacquer or High Build Lacquer.

SHELF LIFE

1 year

CLEAN-UP

Clean up with EdgeChem Lacquer Thinner.

